

Vetsoorten

Merk	Specificatie	Druppel- punt	Penetratie bij 25C°	Werktemperatuur C°	Opmerking
China Hangu	Hangu 2#	198	265~295	-10~130	laag geluid
China Jingzhi	HTHS	300	280	-40~200	lage en hoge temperatuur
Chevron	SRI-2	240	255~280	-30~120	water bestendig
Shell	Alvania R2	185	265~295	-35~120	
	Alvania R3	185	220~250	-35~135	
	Alvania R A	180	250~275	-25~100	algemene toepassing
	Alvania EP1	180	310~340	-25~110	
	Alvania EP2	185	265~295	-25~110	water bestendig
	Darina 2	250	265~295	-25~150	
	Darina EP2	250	265~295	-25~150	hoge temperatuur
	Dolium R 2	250	265~295	-35~150	corrosie bestendig
	Cassida RLS1	150	310~300	-40~120	levensmiddelenvet, lage temp, 1vet
	Cassida RLS2	150	265~295	-35~120	levensmiddelenvet, lage temp, 2vet
Klüber	Barrierta L55/2	420	450	-40~260	hoge temperatuur
	Isoflex LDS 18	190	255~280	-50~110	lage temperatuur
	Isoflex PDL300A	250	280	-70~110	lage temperatuur (Lithium)
	Isoflex NBU 15	250	255~280	-30~120	hoge toeren, geen kunst kooi (Syn)
	Isoflex Topas NCA52	220	265~295	-50~150	lage temperatuur (Syn)
	Straburags NBU12K	200	260	-30~150	zeewaterbesteding (Min)
	UH1 14/222	250	310~340	-45~120	levensmiddelenvet (Syn)
Kyodo Yushi	Multemp SRL	185	225~245	-40~145	laag koppel
	Multemp PS2	190	250~275	-50~110	lage temperatuur
	Multemp SC-2	260	255~280	0~160	
	Multemp ET150	260	255~280	-10~160	hoge temperatuur
Esso	Andok C	260	190~210	-30~120	algemene toepassing
	Andok 260	190	204~260	-40~120	
	Beacon 325	190	255~280	-54~120	lage temperatuur
Mobile	Mobilux 2	190	265~290	-10~110	algemene toepassing
	Mobil 22	192	250~274	-40~120	
	Mobil 28	260	265~295	-55~175	groot temperatuursbereik
	Mobil 48	260	240~270	60~170	hoge temperatuur
	Pharma White 30	250	-	-30~110	levensmiddelen (lijnolie)

